
Calumen® II 1.3.3 22 August 2016 Data base : SGG UK







	First glazing	Second glazing	Third glazing
Gas		Krypton 92% 12.00mm	Krypton 92% 12.00mm
Coating		PLANITHERM TOTAL+	PLANITHERM TOTAL+
First glass	PLANICLEAR 3.00mm	PLANICLEAR 4.00mm	PLANICLEAR 4.00mm
Coating			
Layer	PVB standard 0.76 mm		
Coating			
Second glass	PLANICLEAR 3.00mm		
Coating			

ound transmission loss		
Acoustics simulated values :	Rw(	.) not available
lanufacturing sizes		<b>A</b>
Nominal thickness :	38.8	mm
Weight :	35.8	kg/m <sup>2</sup>
uminous factors (EN410-2011) : (D65 2°)		
Transmittance :	72	%
Outdoor reflectance :	15	70 %
Indoor reflectance :	16	%
	10	//
nergy factors (EN410-2011) :		
Transmittance :	48	%
Outdoor reflectance :	20	%
Indoor reflectance :	25	%
Absorptance A1 :	18	%
Absorptance A2 :	9	%
Absorptance A3 :	6	%
olar factors (EN410-2011) :		
g:	0.58	
Shading coefficient :	0.66	
hermal transmission (EN673-2011) - 0° related to ve	ertical po	osition
Ug :	0.5	W/(m².K)
Ug .	0.5	w(m.x)
Steve Massey		Phone : 01942 262162 Mobile : 07970 137136
Regency Glass Ltd Sales		Fax : 01942 261555
Butts Street		stevemassey@regencyglass.co.uk
umen'll WN7 3AE Leigh		

These values are calculated according to EN410-2011 and EN673-2011 standards. Tolerances are defined according to EN 1096-4 or ISO9050-2003 standards. Nevertheless, user must check the feasibility of the associated products, in particular in terms of thickness and colour. Furthermore, it is his responsibility to check that the resulting combination of glazing meets regulatory requirements at national, local or regional level. Computed values with NFRC-2010 standards are indicative. Please use NFRC certified software for certified values.

Calculation rules and functional output of Calumen II have been validated by TÜV Rheinland Quality Report 11923R-11-33705