





	First glazing	Second glazing
Gas		Argon 90% 12.00mm
Coating		PLANITHERM TOTAL+
First glass	DIAMANT 3.00mm	PLANICLEAR 10.00mm
Coating		
Layer	PVB standard 0.76 mm	
Coating		
Second glass	PLANICLEAR 3.00mm	
Coating		

Sound transmission lo	DSS		
	Acoustics simulated values :	Rw(	.) not available
Manufacturing sizes			Ċ
	Nominal thickness :	28.8	mm
	Weight :		kg/m <sup>2</sup>
Luminous factors (EN	410-2011) : (D65 2°)		
	Transmittance :	70	0/
	Outdoor reflectance :	79 12	%
	Indoor reflectance :	12	70 %
	indoor renectance .	12	<sup>9</sup> / <sub>0</sub>
Energy factors (EN410	0-2011) :		
	- ··· A		
	Transmittance :	57	%
	Outdoor reflectance :	16	%
	Indoor reflectance :	17	%
	Absorptance A1 :	15	%
	Absorptance A2 :	12	%
Solar factors (EN410-2	2011):		
	g:	0.67	
	Shading coefficient :	0.77	
Thermal transmission	(EN673-2011) - 0° related to ve	rtical po	osition
	Ug :	1.3	W/(m².K)
	Massev		Phone · 01942 262162



Steve Massey Regency Glass Ltd Sales Butts Street WN7 3AE Phone : Mobile : Fax : stevemassey@regencyglass.co.uk



CALUMEN® II is a simulation software to calculate key performance of glass such as light transmission, solar factor or thermal insulation coefficient. Computed values are indicative and subject to change. They can not be used to guarantee performance of the products.

Leigh

These values are calculated according to EN410-2011 and EN673-2011 standards. Tolerances are defined according to EN 1096-4 or ISO9050-2003 standards. Nevertheless, user must check the feasibility of the associated products, in particular in terms of thickness and colour. Furthermore, it is his responsibility to check that the resulting combination of glazing meets regulatory requirements at national, local or regional level. Computed values with NFRC-2010 standards are indicative. Please use NFRC certified software for certified values.



