



Pane 1	PLANICLEAR (6 mm)
Cavity 1	ARGON (90%) / AIR (10%) / 18 mm
Pane 2	PLANITHERM TOTAL+ FG PLANICLEAR (4 mm)

Regency Glass Ltd  
Steven Massey

stevemassey@regencyglass.co.uk

 **LUMINOUS FACTORS** CIE (15-2004)

Light transmission (TL %)	79 %
Outdoor reflection (RLe %)	13 %
Indoor (RLi %)	12 %

 **SOLAR FACTORS** EN410 (2011-04)


Solar factor (g)	0.71
Shading Coefficient (SC)	0.82

 **COLOR RENDERING** CIE (15-2004)

Transmission (Ra)	99.0
Reflection (Ra)	89.8

 **BURGLAR RESIST** EN356

Result :	NPD
----------	-----

 **ENERGY FACTORS** EN410 (2011-04)

Transmission (Te)	63 %
Reflection (Ree)	19 %
Indoor (Rei)	20 %
Absorption (AE1)	9 %
Absorption (AE2)	9 %

 **THERMAL TRANSMISSION** EN673 (2011-04)


Ug	1.2 W/m².K
0° related to vertical position	

 **MANUFACTURING SIZES**

Nominal thickness	28.0 mm
Weight	25 kg/m²

 **PENDULUM RESISTANCE** EN12600

Result :	NPD
----------	-----

 **ACOUSTICS** EN12758

Acoustic values according to EN 12758 and from notified body -	Rw(C;Ctr) = 35(-2;-5) dB
OITC (ASTM E1332)	N/A
STC (ASTM E413)	N/A